



C030 - 2K Smooth Clear

North American Market Only

Description:

The C030 2K Smooth Clear is a fast drying, extremely user friendly product suitable for overall re-sprays as well as panel refinishing.



Suitable Substrates:

- Hymax basecoat

Mix 4:1 with any of the following GenMax hardeners:

- H36 2K Hardener Slow
- H23 2K Hardener Normal
- H15 2K Hardener Fast

Potlife: 6h at 20°C (68°F)



17-19s / # 2 Zahn @ 68°F



Compliant 1.3 – 1.5 mm (2 spray passes)
2.5 bar inlet pressure (36 PSI)



HVLP 1.3 – 1.5 mm (2 spray passes)
0.7 bar atomization pressure (10 PSI)



0.8-1.0 Mil per full coat



Wait 12 min before increasing temperature
Bake 20 min at 60 °C (140°F) panel temperature

Product Data Sheet



C030 - 2K Smooth Clear

North American Market Only



Short Wave 8 min
The object should be maintained at greater than 60 cm from source.



Wear suitable protection

VOC: Regulatory VOC 545.6 gr/lit (4.54 lbs/gal)
Regulatory VOC ready to spray < 530.5 gr/lit (4.4 lbs/gal)
P.S: For VOC compliance national rule, ready to spray basecoat needs to be <= 739 grams/liter (6.15 lbs/gal)

Specific Gravity: 0.931 kg/lit (7.75 lbs/gal)

Solids Content: 36.0 – 37.0 % by weight RFU

Coverage: 490 ft²/gal at 1 dry mil dry film thickness (theoretical)

SDS: See the safety data sheet

Product Data Sheet